

## **Product Table:** Small Size Finishing Tools

Material	Туре	Edge Type	RPM	IPM by Cutter Diameter				Depth of Cut	
					.196 (5mm)	.393 (10mm)	0.500	Radial	Axial
	Aluminum Core ≤ 6% Density	Smooth, Stagger Tooth	18000	Finish	30	30	50	.1 x Dia	.015"035"
	Aluminum Core ≥ 6% Density	Stagger Tooth, Sawtooth	18000	Finish	30	30	50	.1 x Dia	.015"035"
	Nomex	Smooth, Stagger Tooth	18000-24000	Finish	150-300	150-300	150-300	.1 x Dia	.050"

## **Product Notes:**

Aluminum Core: Use Conventional direction at all times unless beveling to a sharp edge. Recommend .25° to 2° Lead angle on all cuts. If using 3 axis machine, 0° degree can be used for facing. Watch cutting edges of tools closely to avoid grabbing "ribbons" which can cause severe damage to part. Standard "backers" such as peel ply are recommended if available. Also, application of hot glue bead around stock edges to strengthen workholding is recommended where applicable.

Nomex: Use Conventional direction at all times unless beveling to a sharp edge. Recommend .5° to 2° Lead angle on all cuts. If using 3 axis machine, 0° degree can be used for facing. Watch cutting edges of tools closely to avoid grabbing "ribbons" which can cause severe damage to part. Standard "backers" such as peel ply are recommended if available.

## **General Notes:**

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions.

If you require additional information, Corehog has a team of technical experts available to assist you through even the most challenging applications. Please contact us at 833-584-3448 or corehogtech@harveyperformance.com

WARNING: Cutting tools may shatter under improper use. Government regulations require the use of safety glasses and other appropriate safety equipment in the vicinity of