



Speeds & Feeds

**Product Table:** Variable Helix End Mills for Aluminum Alloys - Ball

**Characteristics:** 3x Length of Cut

**Series:** 9775xx, 9897xx, 9898xx, 9775xx-C8, 9897xx-C8, 9898xx-C8, 9755xx-C4, 9897xx-C4, 9898xx-C4

Cutter Series	MATERIAL	SFM	Chip Load (IPT) By Cutter Diameter											Depth of Cut			
			0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	Radial	Axial	
Uncoated	<b>ALUMINUM ALLOYS</b>																
	Casting (2xx, 5xx, 7xx, 8xx)	750	Slotting	.00020	.00041	.00062	.00082	.00103	.00123	.00165	.00247	.00330	.00432	.00520	.00693	1x Dia	.5x Dia
	Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000	Roughing	.00023	.00048	.00072	.00095	.00120	.00143	.00193	.00288	.00385	.00505	.00606	.00809	.5x Dia	.5x - 1x Dia
	<b>MAGNESIUM ALLOYS</b>	1500	Finishing	.00025	.00051	.00078	.00102	.00129	.00153	.00206	.00309	.00413	.00541	.00650	.00866	.1x Dia	.5x - 1x Dia
	<b>ZINC ALLOYS</b>	800	Max	.00026	.00055	.00083	.00109	.00137	.00164	.00220	.00329	.00440	.00577	.00693	.00924	-	-
	<b>COPPER ALLOYS</b>																
	High Coppers - 90%+ (C1xxxx)	225	Slotting	.00016	.00033	.00050	.00065	.00082	.00098	.00132	.00197	.00264	.00346	.00416	.00554	1x Dia	.5x Dia
	Brass (Copper Zinc alloys, C2xxxx, C3xxxx, C4xxxx, C66400-C69800)	500	Roughing	.00018	.00038	.00058	.00076	.00096	.00115	.00154	.00230	.00308	.00404	.00485	.00647	.5x Dia	.5x - 1x Dia
	Phosphor Bronzes (Copper Tin alloys, C5xxxx)	225															
	Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	500	Finishing	.00020	.00041	.00062	.00082	.00103	.00123	.00165	.00247	.00330	.00432	.00520	.00693	.1x Dia	.5x - 1x Dia
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500																
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxxx)	225	Max	.00021	.00044	.00066	.00087	.00110	.00131	.00176	.00263	.00352	.00461	.00554	.00739	-	-	
Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95800, C97300-C97800, C99400-C99700)	550																
TiB2	<b>ALUMINUM ALLOYS</b>																
	Casting (2xx, 5xx, 7xx, 8xx)	1000	Slotting	.00026	.00053	.00081	.00106	.00134	.00160	.00215	.00321	.00429	.00562	.00676	.00901	1x Dia	.5x Dia
	Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1400	Roughing	.00030	.00062	.00094	.00124	.00156	.00186	.00250	.00374	.00501	.00656	.00788	.01051	.5x Dia	.5x - 1x Dia
	<b>MAGNESIUM ALLOYS</b>	2000	Finishing	.00032	.00066	.00101	.00133	.00167	.00199	.00268	.00401	.00536	.00703	.00845	.01126	.1x Dia	.5x - 1x Dia
<b>ZINC ALLOYS</b>	1100	Max	.00034	.00071	.00108	.00142	.00178	.00213	.00286	.00428	.00572	.00750	.00901	.01201			
Amorphous Diamond	<b>ALUMINUM (High Silicon)</b>																
	Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	2500	Slotting	.00022	.00045	.00068	.00090	.00113	.00135	.00182	.00272	.00363	.00476	.00572	.00762	1x Dia	.4x Dia
	Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	2000	Roughing	.00025	.00053	.00080	.00105	.00132	.00158	.00212	.00317	.00424	.00555	.00667	.00889	.4x Dia	.3x - .8x Dia
	Casting - 8%-12% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	1500															
	Casting - 12%-16% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	1000	Finishing	.00027	.00056	.00085	.00113	.00142	.00169	.00227	.00339	.00454	.00595	.00715	.00953	.1x Dia	.5x - 1x Dia
	Wrought - 5%-8% Si (4xxx)	2200	Max	.00029	.00060	.00091	.00120	.00151	.00180	.00242	.00362	.00484	.00634	.00762	.01016	-	-
	Wrought - 8%-12% Si (4xxx)	1700															
	<b>COPPER ALLOYS</b>																
	High Coppers - 90%+ (C1xxxx)	800	Slotting	.00017	.00036	.00055	.00072	.00091	.00108	.00145	.00217	.00290	.00381	.00457	.00610	1x Dia	.4x Dia
	Brass (Copper Zinc alloys, C2xxxx, C3xxxx, C4xxxx, C66400-C69800)	1500															
	Phosphor Bronzes (Copper Tin alloys, C5xxxx)	800	Roughing	.00020	.00042	.00064	.00084	.00106	.00126	.00169	.00253	.00339	.00444	.00534	.00711	.4x Dia	.3x - .8x Dia
	Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	1000															
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	1000	Finishing	.00022	.00045	.00068	.00090	.00113	.00135	.00182	.00272	.00363	.00476	.00572	.00762	.1x Dia	.5x - 1x Dia	
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxxx)	800																
Cast Copper Alloys (C80100-C82800, C86300, C90200-C91700, C96200-C96600, C99300)	150	Max	.00023	.00048	.00073	.00096	.00121	.00144	.00194	.00290	.00387	.00507	.00610	.00813	-	-	
Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95800, C97300-C97800, C99400-C99700)	750																

**Please note:**  
 All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed.  
 If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or **Harveytech@harveyperformance.com**.  
 WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.