

| Chamfer Mills | | | | | | | | | |
|------------------------------------|---|------|------------|----------------|--------------|--------------|--------------|--------------|-------------|
| Material Guide | | HRc | SFM | FEED PER TOOTH | | | | | |
| | | | | UP TO 1/8" | 1/8" - 3/16" | 3/16" - 1/4" | 1/4" - 5/16" | 5/16" - 3/8" | 3/8" - 1/2" |
| COBALT BASE ALLOYS | Stellite, HS-21, Haynes 25/188, X-40, L-605 | < 32 | 30 - 50 | .0004 | .0005 | .0010 | .0010 | .0010 | .0010 |
| NICKEL BASE ALLOYS | Inconel-625/718, Waspalloy, Rene, Hastelloy | < 32 | 30 - 50 | .0004 | .0005 | .0010 | .0010 | .0010 | .0010 |
| IRON BASE ALLOYS | Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpeneter 22-b3 | < 32 | 40 - 65 | .0005 | .0005 | .0010 | .0010 | .0015 | .0020 |
| TITANIUM ALLOYS | Commercially Pure, 6AL-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si | | 25 - 125 | .0005 | .0005 | .0005 | .0005 | .0010 | .0010 |
| STAINLESS STEEL (PRECIPITATION) | 13/8, 15/5, 17-4, AM-350/355 | < 32 | 40 - 125 | .0005 | .0005 | .0010 | .0010 | .0010 | .0020 |
| STAINLESS STEEL (AUSTENITIC) | 200 Series, 302, 303, 304, 316, 304L, 316L | < 32 | 50 - 175 | .0001 | .0002 | .0005 | .0005 | .0010 | .0015 |
| STAINLESS STEEL (MARTENSITIC) | 403, 410, 416, 440 | < 32 | 50 - 125 | .0001 | .0002 | .0005 | .0005 | .0005 | .0010 |
| HIGH STRENGTH TOOL STEELS | 4140, 4340, 6150, 5210, A2, D2 P20, H11, H13, S2, 01 | < 32 | 25 - 150 | .0005 | .0005 | .0010 | .0010 | .0010 | .0010 |
| MEDIUM ALLOY STEELS | 200, 250, 300 | < 32 | 75 - 175 | .0005 | .0005 | .0010 | .0010 | .0020 | .0025 |
| CARBON STEELS | A36, 12L14, 12L15, 1005, 1018, 1020, 1108-1119, 1213-1215, 1513-1518, 4012, 5015, 9310 | < 32 | 50 - 200 | .0005 | .0010 | .0015 | .0015 | .0020 | .0030 |
| DUCTILE | Ductile Cast Irons | | 50 - 200 | .0005 | .0010 | .0015 | .0015 | .0020 | .0020 |
| CAST IRONS | Gray Cast Irons | | 50 - 200 | .0005 | .0010 | .0020 | .0020 | .0030 | .0040 |
| ALUMINUM | 2014, 2024, 6061-(T1-T6), 7075, Die Cast, Extruded | | 500 - 1000 | .0010 | .0020 | .0020 | .0020 | .0030 | .0040 |
| MAGNESIUM | | | 450 - 650 | .0010 | .0020 | .0020 | .0020 | .0030 | .0040 |
| COPPER, COPPER ALLOYS | Yellow Brass, High Lead Brass, Red Brass | | 400 - 750 | .0010 | .0010 | .0020 | .0020 | .0025 | .0030 |
| BRASS, BRONZE | Brass, Alum/Bronze, Low Silicon Bronze | | 400 - 500 | .0010 | .0010 | .0020 | .0020 | .0025 | .0030 |
| PLASTICS | Acrylics, Phenolics | | 100 - 300 | .0010 | .0020 | .0030 | .0030 | .0040 | .0060 |
| CARBON, GRAPHITES | | | 100 - 200 | .0040 | .0040 | .0060 | .0060 | .0080 | .0100 |