



Product Table: Miniature End Mills - Square - Long Reach, Standard Flute
Characteristics: 10x Reach Multiple, 4 Flutes
Series: 8461xx, 8462xx

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 10% -20% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 10% -20%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or Harveytech@harveyperformance.com.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.

MATERIAL		Hardness: ≤ 28 Rc (≤ 271 HBn)															
		SFM	Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia						Depth of Cut			
			0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187	0.250	0.375	0.500	Radial	Axial
ALUMINUM ALLOYS	750	Slotting	.00009	.00019	.00029	1 x Dia	.07 x Dia	.00033	.00042	.00050	.00067	.00100	.00134	.00201	.00268	1 x Dia	.16 x Dia
		Roughing	.00012	.00024	.00036	25 x Dia	.30 x Dia	.00042	.00052	.00062	.00084	.00125	.00168	.00252	.00336	.50 x Dia	.30 x Dia
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000	Finishing	.00020	.00042	.00064	.05 x Dia	3 x Dia	.00073	.00092	.00110	.00148	.00221	.00295	.00443	.00591	.09 x Dia	3 x Dia
	750	Slotting	.00008	.00017	.00026	1 x Dia	.07 x Dia	.00030	.00038	.00045	.00060	.00090	.00121	.00181	.00242	1 x Dia	.16 x Dia
Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	700	Slotting	.00008	.00017	.00026	1 x Dia	.07 x Dia	.00030	.00038	.00045	.00060	.00090	.00121	.00181	.00242	1 x Dia	.16 x Dia
	650	Roughing	.00010	.00022	.00033	25 x Dia	.30 x Dia	.00037	.00047	.00056	.00075	.00113	.00151	.00226	.00302	.50 x Dia	.30 x Dia
Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	475	Slotting	.00008	.00017	.00026	1 x Dia	.07 x Dia	.00030	.00038	.00045	.00060	.00090	.00121	.00181	.00242	1 x Dia	.16 x Dia
	1000	Finishing	.00018	.00038	.00057	.05 x Dia	3 x Dia	.00066	.00083	.00099	.00133	.00199	.00266	.00399	.00532	.09 x Dia	3 x Dia
Wrought - 8%-12% Si (4xxx)	800	Slotting	.00009	.00019	.00029	1 x Dia	.07 x Dia	.00033	.00042	.00050	.00067	.00100	.00134	.00201	.00268	1 x Dia	.16 x Dia
	1500	Roughing	.00012	.00024	.00036	25 x Dia	.30 x Dia	.00042	.00052	.00062	.00084	.00125	.00168	.00252	.00336	.50 x Dia	.30 x Dia
MAGNESIUM ALLOYS	800	Finishing	.00020	.00042	.00064	.05 x Dia	3 x Dia	.00073	.00092	.00110	.00148	.00221	.00295	.00443	.00591	.09 x Dia	3 x Dia
ZINC ALLOYS	800	Finishing	.00020	.00042	.00064	.05 x Dia	3 x Dia	.00073	.00092	.00110	.00148	.00221	.00295	.00443	.00591	.09 x Dia	3 x Dia
COPPER ALLOYS	225	Slotting	.00007	.00015	.00023	1 x Dia	.07 x Dia	.00027	.00033	.00040	.00054	.00080	.00107	.00161	.00215	1 x Dia	.16 x Dia
High Coppers - 90%+ (C1xxx) Brass (Copper Zinc alloys, C2xxx, C3xxx, C4xxx, C66400-C69800) Phosphor Bronzes (Copper Tin alloys, C5xxx)	500	Slotting	.00007	.00015	.00023	1 x Dia	.07 x Dia	.00027	.00033	.00040	.00054	.00080	.00107	.00161	.00215	1 x Dia	.16 x Dia
	225	Slotting	.00007	.00015	.00023	1 x Dia	.07 x Dia	.00027	.00033	.00040	.00054	.00080	.00107	.00161	.00215	1 x Dia	.16 x Dia
Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200) Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500	Roughing	.00009	.00019	.00029	25 x Dia	.30 x Dia	.00033	.00042	.00050	.00067	.00100	.00134	.00201	.00268	.50 x Dia	.30 x Dia
	500	Roughing	.00009	.00019	.00029	25 x Dia	.30 x Dia	.00033	.00042	.00050	.00067	.00100	.00134	.00201	.00268	.50 x Dia	.30 x Dia
Copper Nicksels, Nickel Silvers (Copper Nickel alloys, C7xxx) Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95800, C97300-C97800, C99400-C99700)	225	Slotting	.00007	.00015	.00023	1 x Dia	.07 x Dia	.00027	.00033	.00040	.00054	.00080	.00107	.00161	.00215	1 x Dia	.16 x Dia
	550	Finishing	.00016	.00034	.00051	.05 x Dia	3 x Dia	.00059	.00074	.00088	.00118	.00177	.00236	.00355	.00473	.09 x Dia	3 x Dia

MATERIAL		Hardness: 29-37 Rc (279-344 HBn)															
		SFM	Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia						Depth of Cut			
			0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187	0.250	0.375	0.500	Radial	Axial
CARBON STEELS	600	Slotting	.00003	.00007	.00010	1 x Dia	.07 x Dia	.00011	.00014	.00017	.00023	.00034	.00046	.00069	.00092	1 x Dia	.16 x Dia
		Roughing	.00004	.00007	.00011	25 x Dia	.30 x Dia	.00013	.00016	.00019	.00026	.00039	.00052	.00078	.00104	.50 x Dia	.30 x Dia
		Finishing	.00006	.00013	.00020	.05 x Dia	3 x Dia	.00023	.00029	.00034	.00046	.00069	.00092	.00139	.00185	.09 x Dia	3 x Dia
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xxx, 3xxx, 4xxx & 4Lxx, 5xxx & 5Lxx, 50xxx & 50Lxx, 51xxx & 51Lxx, 52xxx & 52Lxx, 6xxx, 8xx, 9xxx	200	Slotting	.00003	.00006	.00009	1 x Dia	.07 x Dia	.00010	.00013	.00016	.00021	.00032	.00042	.00063	.00084	1 x Dia	.16 x Dia
		Roughing	.00003	.00007	.00010	25 x Dia	.30 x Dia	.00012	.00015	.00018	.00024	.00035	.00047	.00071	.00095	.50 x Dia	.30 x Dia
		Finishing	.00006	.00012	.00018	.05 x Dia	3 x Dia	.00021	.00026	.00031	.00042	.00063	.00084	.00127	.00169	.09 x Dia	3 x Dia
STAINLESS STEELS	450	Slotting	.00003	.00007	.00010	1 x Dia	.07 x Dia	.00011	.00014	.00017	.00023	.00034	.00046	.00069	.00092	1 x Dia	.16 x Dia
		Roughing	.00004	.00007	.00011	25 x Dia	.30 x Dia	.00013	.00016	.00019	.00026	.00039	.00052	.00078	.00104	.50 x Dia	.30 x Dia
		Finishing	.00006	.00013	.00020	.05 x Dia	3 x Dia	.00023	.00029	.00034	.00046	.00069	.00092	.00139	.00185	.09 x Dia	3 x Dia
201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	200	Slotting	.00003	.00006	.00009	1 x Dia	.07 x Dia	.00010	.00013	.00016	.00021	.00032	.00042	.00063	.00084	1 x Dia	.16 x Dia
		Roughing	.00003	.00007	.00010	25 x Dia	.30 x Dia	.00012	.00015	.00018	.00024	.00035	.00047	.00071	.00095	.50 x Dia	.30 x Dia
		Finishing	.00006	.00012	.00018	.05 x Dia	3 x Dia	.00021	.00026	.00031	.00042	.00063	.00084	.00127	.00169	.09 x Dia	3 x Dia
414, 431, 440A, 440B, 440C, 13-8, 15-5, 15-7, 17-4, 17-7	150	Slotting	.00002	.00004	.00006	1 x Dia	.07 x Dia	.00007	.00008	.00010	.00013	.00020	.00026	.00040	.00053	1 x Dia	.16 x Dia
		Roughing	.00002	.00004	.00006	25 x Dia	.30 x Dia	.00007	.00009	.00011	.00015	.00022	.00030	.00044	.00059	.50 x Dia	.30 x Dia
		Finishing	.00004	.00008	.00011	.05 x Dia	3 x Dia	.00013	.00016	.00020	.00026	.00039	.00053	.00079	.00106	.09 x Dia	3 x Dia
TOOL STEELS	200	Slotting	.00003	.00006	.00009	1 x Dia	.07 x Dia	.00010	.00013	.00016	.00021	.00032	.00042	.00063	.00084	1 x Dia	.16 x Dia
		Roughing	.00003	.00007	.00010	25 x Dia	.30 x Dia	.00012	.00015	.00018	.00024	.00035	.00047	.00071	.00095	.50 x Dia	.30 x Dia
		Finishing	.00006	.00012	.00018	.05 x Dia	3 x Dia	.00021	.00026	.00031	.00042	.00063	.00084	.00127	.00169	.09 x Dia	3 x Dia
A, L, O, P, W series	150	Slotting	.00002	.00004	.00006	1 x Dia	.07 x Dia	.00007	.00008	.00010	.00013	.00020	.00026	.00040	.00053	1 x Dia	.16 x Dia
		Roughing	.00002	.00004	.00006	25 x Dia	.30 x Dia	.00007	.00009	.00011	.00015	.00022	.00030	.00044	.00059	.50 x Dia	.30 x Dia
		Finishing	.00004	.00008	.00011	.05 x Dia	3 x Dia	.00013	.00016	.00020	.00026	.00039	.00053	.00079	.00106	.09 x Dia	3 x Dia
D, H, M, T, S series	150	Slotting	.00002	.00004	.00006	1 x Dia	.07 x Dia	.00007	.00008	.00010	.00013	.00020	.00026	.00040	.00053	1 x Dia	.16 x Dia
		Roughing	.00002	.00004	.00006	25 x Dia	.30 x Dia	.00007	.00009	.00011	.00015	.00022	.00030	.00044	.00059	.50 x Dia	.30 x Dia
		Finishing	.00004	.00008	.00011	.05 x Dia	3 x Dia	.00013	.00016	.00020	.00026	.00039	.00053	.00079	.00106	.09 x Dia	3 x Dia
TITANIUM ALLOYS	150	Slotting	.00002	.00004	.00006	1 x Dia	.07 x Dia	.00007	.00008	.00010	.00013	.00020	.00026	.00040	.00053	1 x Dia	.16 x Dia
		Roughing	.00002	.00004	.00006	25 x Dia	.30 x Dia	.00007	.00009	.00011	.00015	.00022	.00030	.00044	.00059	.50 x Dia	.30 x Dia
		Finishing	.00004	.00008	.00011	.05 x Dia	3 x Dia	.00013	.00016	.00020	.00026	.00039	.00053	.00079	.00106	.09 x Dia	3 x Dia
HIGH TEMP ALLOYS	70	Slotting	.00002	.00004	.00006	1 x Dia	.07 x Dia	.00007	.00008	.00010	.00013	.00020	.00026	.00040	.00053	1 x Dia	.16 x Dia
		Roughing	.00002	.00004	.00006	25 x Dia	.30 x Dia	.00007	.00009	.00011	.00015	.00022	.00030	.00044	.00059	.50 x Dia	.30 x Dia
		Finishing	.00004	.00008	.00011	.05 x Dia	3 x Dia	.00013	.00016	.00020	.00026	.00039	.00053	.00079	.00106	.09 x Dia	3 x Dia

MATERIAL		Hardness: 38-45 Rc (353-421 HBn)															
		SFM	Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia						Depth of Cut			
			0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187	0.250	0.375	0.500	Radial	Axial
CARBON STEELS	600	Slotting	.00003	.00007	.00010	1 x Dia	.07 x Dia	.00011	.00014	.00017	.00023	.00034	.00046	.00069	.00092	1 x Dia	.16 x Dia
		Roughing	.00004	.00007	.00011	25 x Dia	.30 x Dia	.00013	.00016	.00019	.00026	.00039	.00052	.00078	.00104	.50 x Dia	.30 x Dia
		Finishing	.00006	.00013	.00020	.05 x Dia	3 x Dia	.00023	.00029	.00034	.00046	.00069	.00092	.00139	.00185	.09 x Dia	3 x Dia
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xxx, 3xxx, 4xxx & 4Lxx, 5xxx & 5Lxx, 50xxx & 50Lxx, 51xxx & 51Lxx, 52xxx & 52Lxx, 6xxx, 8xx, 9xxx	200	Slotting	.00003	.00006	.00009	1 x Dia	.07 x Dia	.00010	.00013	.00016	.00021	.00032	.00042	.00063	.00084	1 x Dia	.16 x Dia
		Roughing	.00003	.00007	.00010	25 x Dia	.30 x Dia	.00012	.00015	.00018	.00024	.00035	.00047	.00071	.00095	.50 x Dia	.30 x Dia
		Finishing	.00006	.00012	.00018	.05 x Dia	3 x Dia	.00021	.00026	.00031	.00042	.0					