

SPEEDS & FEEDS

3 Flute

HST-3

HST-3 / HST-RN-3																	
Material Guide		Hardness	SFM	Inches per Tooth (IPT)													
				1/8		3/16		1/4		3/8		1/2		3/4		1	
				Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh
Carbon Steel	10XX, 11XX, 12XX, 12LXX, ASTM A27, ASTM A36	< 75 HRB	455	.0007	.0011	.0010	.0017	.0013	.0023	.0019	.0034	.0025	.0044	.0036	.0064	.0045	.0082
		75 - 98 HRB	445	.0005	.0009	.0007	.0013	.0009	.0017	.0014	.0025	.0018	.0032	.0026	.0047	.0033	.0060
		21 - 36 HRC	400	.0003	.0006	.0005	.0008	.0006	.0011	.0009	.0016	.0012	.0021	.0017	.0030	.0021	.0039
Low Alloy Steel	13XX, 41XX, 43XX, 51XX, 86XX, 93XX	75 - 98 HRB	390	.0004	.0007	.0006	.0011	.0008	.0015	.0012	.0022	.0016	.0028	.0023	.0041	.0029	.0052
		21 - 36 HRC	340	.0003	.0005	.0005	.0008	.0006	.0011	.0009	.0016	.0012	.0021	.0017	.0030	.0021	.0039
		36 - 50 HRC	260	.0003	.0005	.0004	.0007	.0005	.0009	.0008	.0014	.0010	.0018	.0015	.0026	.0019	.0034
Tool Steel	A2, H13, L6, P20, S7	> 50 HRC	155	.0002	.0004	.0003	.0006	.0004	.0007	.0006	.0011	.0008	.0014	.0012	.0021	.0015	.0027
		75 - 98 HRB	340	.0004	.0007	.0006	.0011	.0008	.0015	.0012	.0022	.0016	.0028	.0023	.0041	.0029	.0052
		21 - 36 HRC	250	.0003	.0006	.0005	.0009	.0007	.0011	.0010	.0017	.0013	.0022	.0018	.0032	.0023	.0041
Specialty Steel	300M, Invar 36, Kovar, Maraging 200, Maraging 250, Maraging 300, Maraging 350	> 50 HRC	85	.0002	.0004	.0003	.0006	.0004	.0007	.0006	.0011	.0008	.0014	.0012	.0021	.0015	.0026
		75 - 98 HRB	340	.0004	.0007	.0006	.0011	.0008	.0015	.0012	.0022	.0016	.0028	.0023	.0041	.0029	.0052
		21 - 36 HRC	250	.0003	.0006	.0005	.0009	.0007	.0011	.0010	.0017	.0013	.0022	.0018	.0032	.0023	.0041
Austenitic Stainless Steel	Nitronic 50, Nitronic 60, 301, 303, 304, 304L, Incoloy 27-7MO, 316, 316L, 321, 347	> 50 HRC	55	.0002	.0003	.0003	.0005	.0004	.0007	.0005	.0010	.0007	.0012	.0010	.0018	.0013	.0023
		75 - 98 HRB	265	.0004	.0007	.0006	.0011	.0008	.0014	.0012	.0021	.0015	.0027	.0022	.0040	.0028	.0051
		21 - 36 HRC	225	.0004	.0006	.0006	.0010	.0007	.0013	.0011	.0019	.0014	.0025	.0020	.0036	.0025	.0046
Martensitic & Ferritic Stainless Steel	403, 410, 416, 420, 440, 430, 446	75 - 98 HRB	300	.0004	.0007	.0006	.0011	.0008	.0015	.0012	.0022	.0016	.0028	.0023	.0041	.0029	.0052
		21 - 36 HRC	280	.0004	.0006	.0005	.0010	.0007	.0013	.0011	.0019	.0014	.0024	.0020	.0035	.0025	.0045
		PH Stainless Steel	200	.0003	.0005	.0005	.0008	.0006	.0011	.0009	.0016	.0012	.0021	.0017	.0030	.0021	.0038
Gray Cast Iron	SAE J431, ASTM A48	75 - 98 HRB	410	.0007	.0012	.0010	.0018	.0013	.0023	.0020	.0035	.0026	.0045	.0037	.0066	.0047	.0084
		21 - 36 HRC	370	.0004	.0006	.0005	.0010	.0007	.0013	.0011	.0019	.0014	.0025	.0020	.0036	.0025	.0046
		Malleable Cast Iron	345	.0004	.0008	.0006	.0011	.0008	.0015	.0012	.0022	.0016	.0029	.0023	.0042	.0030	.0054
Nodular (Ductile) Cast Iron	ASTM A47, ASTM A220, ASTM A602	75 - 98 HRB	310	.0005	.0008	.0007	.0012	.0009	.0015	.0013	.0023	.0017	.0030	.0024	.0043	.0031	.0056
		21 - 36 HRC	260	.0003	.0005	.0004	.0008	.0006	.0010	.0009	.0015	.0011	.0020	.0016	.0029	.0020	.0037
		36 - 50 HRC	135	.0002	.0003	.0003	.0005	.0004	.0007	.0005	.0010	.0007	.0013	.0010	.0018	.0013	.0023
Pure Nickel	Nickel 200, Nickel 201	< 75 HRB	285	.0006	.0010	.0008	.0015	.0011	.0020	.0017	.0030	.0022	.0038	.0031	.0056	.0040	.0072
		75 - 98 HRB	250	.0005	.0008	.0007	.0013	.0009	.0017	.0014	.0025	.0018	.0032	.0026	.0047	.0033	.0060
		Nickel Alloy	80	.0003	.0005	.0004	.0008	.0006	.0010	.0008	.0015	.0011	.0020	.0016	.0029	.0020	.0036
Titanium Alloy	Ti 3Al-2.5V, Ti 6Al-4V, Ti 10V-2Fe-3Al	75 - 98 HRB	80	.0003	.0005	.0004	.0008	.0006	.0010	.0008	.0015	.0011	.0020	.0016	.0029	.0020	.0036
		21 - 36 HRC	75	.0003	.0005	.0004	.0007	.0006	.0010	.0008	.0015	.0011	.0019	.0015	.0027	.0019	.0035
		36 - 50 HRC	70	.0002	.0004	.0004	.0006	.0005	.0008	.0007	.0013	.0009	.0016	.0013	.0023	.0017	.0030
Pure Titanium	Ti Grade 1, Ti Grade 2, Ti Grade 3, Ti Grade 4, Ti Grade 7, Ti Grade 12	< 75 HRB	300	.0008	.0014	.0012	.0021	.0015	.0027	.0023	.0041	.0030	.0053	.0043	.0077	.0055	.0099
		75 - 98 HRB	275	.0007	.0012	.0010	.0018	.0013	.0023	.0019	.0034	.0025	.0045	.0036	.0065	.0046	.0083
		21 - 36 HRC	250	.0005	.0009	.0007	.0013	.0010	.0017	.0014	.0026	.0019	.0033	.0027	.0049	.0034	.0062
Cobalt Alloy	ASTM F562, ASTM F90, ASTM F75, ASTM F799	75 - 98 HRB	180	.0004	.0007	.0006	.0010	.0008	.0014	.0011	.0020	.0015	.0026	.0021	.0038	.0027	.0049
		21 - 36 HRC	160	.0004	.0006	.0005	.0009	.0007	.0012	.0010	.0019	.0014	.0024	.0019	.0035	.0025	.0045
		36 - 50 HRC	160	.0004	.0006	.0005	.0009	.0007	.0012	.0010	.0019	.0014	.0024	.0019	.0035	.0025	.0045

Milling Process	Hardness	ADOC	RDOC
Slot (Full Slotting)	< 35 HRC	100%-150% Diameter	100% Diameter
	≥ 35 HRC	100%-125% Diameter	100% Diameter
Rgh (Traditional Roughing)	< 35 HRC	Up to Max LOC	Up to 50% Diameter
	≥ 35 HRC	Up to Max LOC	Up to 50% Diameter

NOTES:

Hardness Scales: HRB = Rockwell B
 HRC = Rockwell C

IPT values shown are for 2.5xD length of cut tools, and should be adjusted for longer or shorter lengths of cut. Values shown are for non-reached tools. For tools with reaches greater than 3xD, IPT should be reduced. For more accurate running parameters, please refer to Machining Advisor Pro.