



Speeds & Feeds

Product Table: End Mills for Steels & High Temp Alloys - Corner Radius - 5 Flute
 End Mills for Steels & High Temp Alloys - Square - 5 Flute - Stub & Standard
 End Mills for Steels & High Temp Alloys - Square - 5 Flute - Variable Helix

Characteristics: 2x, 3x, 4x Length of Cut, 5 & 6 Flutes

Series: ARC-XXX-X-XXX, ARM-XXX-X, ARM-XXXX-X, ARMM-XXX-X, ASM-XXX-X, ASMM-XXX-X, VHM-XXX-X, VHM-XXXX-X

Material	Hardness (HBn)	SFM	Chip Load (IPT) By Cutter Diameter												Depth of Cut		
			0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	Radial	Axial	
Tool Steels: D, H, M, T, S series	350 - 400	100	Slotting	.00005	.00010	.00015	.00019	.00024	.00029	.00039	.00058	.00078	.00102	.00122	.00163	1x Dia	.4x Dia
	400 - 425	80															
Stainless Steels: 40x, 41x, 42x, 43x, 44x, 13-8, 15-5, 15-7, 17-4, 17-7	275 - 300	160	Roughing	.00006	.00012	.00019	.00025	.00031	.00037	.00050	.00075	.00100	.00131	.00158	.00210	.4x Dia	.5x - .7x Dia
	300 - 350	140															
Titanium: All alloys	275 - 300	200	Finishing	.00008	.00016	.00024	.00032	.00041	.00048	.00065	.00097	.00130	.00170	.00205	.00273	.1x Dia	.5x - 1x Dia
	300 - 350	125															
Nickel Alloys: Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	350 - 400	75	Max	.00009	.00020	.00030	.00039	.00049	.00059	.00079	.00118	.00158	.00206	.00248	.00331	-	-
	400 - 425	40															

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed. If you require additional information, Micro100 has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-421-8065** or **micro100tech@harveyperformance.com**.
 WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.