

MATERIAL	SFM	Hardness: ≤ 28 Rc (≤ 271 HBn)										Depth of Cut				
		Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia					Radial	Axial			
		0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187			0.250		
ALUMINUM ALLOYS																
Casting (2xx, 5xx, 7xx, 8xx)	750	Finishing	.00011	.00022	.00034	.05 x Dia	7 x Dia	.00039	.00049	.00058	.00078	.00117	.00156	.10 x Dia	7 x Dia	
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000															
Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	750															
Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	700															
Casting - 8%-12% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	650	Finishing	.00010	.00020	.00030	.05 x Dia	7 x Dia	.00035	.00044	.00052	.00070	.00105	.00141	.10 x Dia	7 x Dia	
Casting - 12%-16% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	475															
Wrought - 5%-8% Si (4xxx)	1000															
Wrought - 8%-12% Si (4xxx)	800															
MAGNESIUM ALLOYS	1500	Finishing	.00011	.00022	.00034	.05 x Dia	7 x Dia	.00039	.00049	.00058	.00078	.00117	.00156	.10 x Dia	7 x Dia	
ZINC ALLOYS	800															
COPPER ALLOYS																
High Coppers - 90%+ (C1xxx)	225															
Brass (Copper Zinc alloys, C2xxx, C3xxx, C4xxx, C66400-C69800)	500															
Phosphor Bronzes (Copper Tin alloys, C5xxx)	225															
Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	500	Finishing	.00009	.00018	.00027	.05 x Dia	7 x Dia	.00031	.00039	.00047	.00063	.00094	.00125	.10 x Dia	7 x Dia	
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500															
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxx)	225															
Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95900, C97300-C97800, C99400-C99700)	550															



Speeds & Feeds

Product Table: Miniature End Mills - Square - Long Flute
Characteristics: 7x Length of Cut, 4 Flutes
Series: 8103xx, 8979xx, and Item # 898008

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 10%-20% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 10%-20%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or Harveytech@harveyperformance.com.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.

MATERIAL	SFM	Hardness: 29-37 Rc (279-344 HBn)										Depth of Cut				
		Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia					Radial	Axial			
		0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187			0.250		
CARBON STEELS																
Free-Machining/Low Carbon steels, 10xx - 1029 & all 10Lxx, 11xx - 1139 & all 11Lxx, 12xx - 1215 & all 12Lxx	600	Finishing	.00003	.00007	.00011	.05 x Dia	7 x Dia	.00012	.00015	.00018	.00024	.00037	.00049	.10 x Dia	7 x Dia	
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xx, 3xx, 4xx & 4xLxx, 5xx & 5xLxx, 50xx & 50Lxx, 51xx & 51Lxx, 52xx & 52Lxx, 6xx, 8xx, 9xx	200	Finishing	.00003	.00006	.00010	.05 x Dia	7 x Dia	.00011	.00014	.00017	.00022	.00033	.00045	.10 x Dia	7 x Dia	
STAINLESS STEELS																
203 EZ, 303 (all types), 416, 416Se, 416 Plus X, 420F, 420FSe, 430F, 430FSe, 440F, 440FSe	450	Finishing	.00003	.00007	.00011	.05 x Dia	7 x Dia	.00012	.00015	.00018	.00024	.00037	.00049	.10 x Dia	7 x Dia	
201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	200	Finishing	.00003	.00006	.00010	.05 x Dia	7 x Dia	.00011	.00014	.00017	.00022	.00033	.00045	.10 x Dia	7 x Dia	
414, 431, 440A, 440B, 440C, 13-8, 15-5, 15-7, 17-4, 17-7	150	Finishing	.00002	.00004	.00006	.05 x Dia	7 x Dia	.00007	.00009	.00010	.00014	.00021	.00028	.10 x Dia	7 x Dia	
TOOL STEELS																
A, L, O, P, W series	200	Finishing	.00003	.00006	.00010	.05 x Dia	7 x Dia	.00011	.00014	.00017	.00022	.00033	.00045	.10 x Dia	7 x Dia	
D, H, M, T, S series	150	Finishing	.00002	.00004	.00006	.05 x Dia	7 x Dia	.00007	.00009	.00010	.00014	.00021	.00028	.10 x Dia	7 x Dia	
TITANIUM ALLOYS																
150	Finishing	.00002	.00004	.00006	.05 x Dia	7 x Dia	.00007	.00009	.00010	.00014	.00021	.00028	.10 x Dia	7 x Dia		
HIGH TEMP ALLOYS																
Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	70	Finishing	.00002	.00004	.00006	.05 x Dia	7 x Dia	.00007	.00009	.00010	.00014	.00021	.00028	.10 x Dia	7 x Dia	

MATERIAL	SFM	Hardness: 38-45 Rc (353-421 HBn)										Depth of Cut				
		Chip Load (IPT) by Dia			Depth of Cut		Chip Load (IPT) by Cutter Dia					Radial	Axial			
		0.015	0.031	0.047	Radial	Axial	0.062	0.078	0.093	0.125	0.187			0.250		
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	100	Finishing	.00002	.00003	.00005	.05 x Dia	7 x Dia	.00006	.00007	.00008	.00011	.00017	.00023	.10 x Dia	7 x Dia	
	90	Finishing	.00001	.00002	.00003	.05 x Dia	7 x Dia	.00003	.00004	.00005	.00007	.00011	.00014	.10 x Dia	7 x Dia	
	100	Finishing	.00002	.00003	.00005	.05 x Dia	7 x Dia	.00006	.00007	.00008	.00011	.00017	.00023	.10 x Dia	7 x Dia	
	90	Finishing	.00001	.00002	.00003	.05 x Dia	7 x Dia	.00003	.00004	.00005	.00007	.00011	.00014	.10 x Dia	7 x Dia	
	75	Finishing	.00001	.00002	.00003	.05 x Dia	7 x Dia	.00003	.00004	.00005	.00007	.00011	.00014	.10 x Dia	7 x Dia	
	50	Finishing	.00001	.00002	.00003	.05 x Dia	7 x Dia	.00003	.00004	.00005	.00007	.00011	.00014	.10 x Dia	7 x Dia	