

MATERIAL	Hardness: ≤ 28 Rc (≤ 271 HBn)													Depth of Cut Passes	
	SFM	Chip Load (IPT) By Effective Cutter Diameter													
			0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	
ALUMINUM ALLOYS															
Casting (2xxx, 5xxx, 7xxx, 8xxx)	750	Deburr	.00015	.00031	.00047	.00063	.00079	.00094	.00126	.00189	.00252	.00315	.00379	.00505	1
		Edge Break	.00013	.00026	.00040	.00052	.00066	.00078	.00105	.00157	.00210	.00263	.00316	.00421	1
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000	Full Chamfer	.00009	.00020	.00030	.00039	.00049	.00059	.00079	.00118	.00158	.00197	.00237	.00316	2
Casting - 3%-5% Si (3xxx, A3xxx, C3xxx, 4xxx, A4xxx, B4xxx)	750	Deburr	.00014	.00028	.00043	.00056	.00071	.00085	.00114	.00170	.00227	.00284	.00341	.00454	1
Casting - 5%-8% Si (3xxx, A3xxx, C3xxx, 4xxx, A4xxx, B4xxx)	700														
Casting - 8%-12% Si (3xxx, A3xxx, C3xxx, 4xxx, A4xxx, B4xxx)	650	Edge Break	.00011	.00023	.00036	.00047	.00059	.00070	.00095	.00142	.00189	.00236	.00284	.00379	1
Casting - 12%-18% Si (3xxx, A3xxx, C3xxx, 4xxx, A4xxx, B4xxx)	475														
Wrought - 5%-8% Si (4xxx)	1000	Full Chamfer	.00009	.00018	.00027	.00035	.00044	.00053	.00071	.00106	.00142	.00177	.00213	.00284	2
Wrought - 8%-12% Si (4xxx)	800														
MAGNESIUM ALLOYS	1500	Deburr	.00015	.00031	.00047	.00063	.00079	.00094	.00126	.00189	.00252	.00315	.00379	.00505	1
		Edge Break	.00013	.00026	.00040	.00052	.00066	.00078	.00105	.00157	.00210	.00263	.00316	.00421	1
ZINC ALLOYS	800	Full Chamfer	.00009	.00020	.00030	.00039	.00049	.00059	.00079	.00118	.00158	.00197	.00237	.00316	2
COPPER ALLOYS															
High Coppers - 90%+ (C1xxxx)	225	Deburr	.00012	.00025	.00038	.00050	.00063	.00075	.00101	.00151	.00202	.00252	.00303	.00404	1
Brass (Copper-Zinc alloys, C2xxxx, C3xxxx, C4xxxx, C66400-C69800)	500														
Phosphor Bronzes (Copper-Tin alloys, C5xxxx)	225														
Aluminum Bronzes (Copper-Aluminum alloys, C60600-C64200)	500	Edge Break	.00010	.00021	.00032	.00042	.00053	.00063	.00084	.00126	.00168	.00210	.00252	.00337	1
Silicon Bronzes (Copper-Silicon alloys, C64700-C66100)	500														
Copper Nickels, Nickel Silvers (Copper-Nickel alloys, C7xxxx)	225														
Cast Copper Alloys (C83300-C86200, C86400-C87800, C92200-C95800, C97300-C97800, C99400-C99700)	550	Full Chamfer	.00008	.00016	.00024	.00031	.00039	.00047	.00063	.00094	.00126	.00158	.00189	.00252	2



Speeds & Feeds

Product Table: Chamfer Cutters - Back Chamfer Cutters

Characteristics: 60° Included Angle, 3x Reach Multiple, 4, 5, and 6 Flutes

Series: 6923xx

Product notes:

Due to a varying diameter, an Effective Cutter Diameter is needed for Chip Load selection and RPM calculation:

Effective Cutter Diameter = (Major Diameter + Minor Diameter)/2.

Or consider the actual diameter along the angle that is engaged with the workpiece.

For Full Chamfer engagement the Effective Cutter Diameter is 80% of the cutter diameter

Depth of Cut is shown as number of Passes with each pass resulting in a descending stepover

Chip Loads are given 3 ways:

Deburring refers to removing the burr only

Traditional Edge Break of .010"-.015"

Full Chamfer engagement

Chip Loads within table pertain to machining on one side an existing slot.

For machining on two sides, reduce Chip Loads to 60%-80% depending on contact length and finish

General notes:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 10%-20% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 10%-20%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or **harveytech@harveyperformance.com**.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other

MATERIAL	SFM	Hardness: 29-37 Rc (279-344 HBn)													Depth of Cut Passes	
		Chip Load (IPT) By Effective Cutter Diameter														
		0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500			
CARBON STEELS	600	Deburr	.00007	.00013	.00020	.00027	.00034	.00040	.00054	.00081	.00108	.00135	.00163	.00217	1	
		Edge Break	.00005	.00011	.00017	.00022	.00028	.00034	.00045	.00068	.00090	.00113	.00136	.00181	1	
		Full Chamfer	.00004	.00008	.00013	.00017	.00021	.00025	.00034	.00051	.00068	.00085	.00102	.00136	3	
	200	Deburr	.00006	.00012	.00019	.00025	.00031	.00037	.00050	.00074	.00099	.00124	.00149	.00198	1	
		Edge Break	.00005	.00010	.00016	.00020	.00026	.00031	.00041	.00062	.00083	.00103	.00124	.00165	1	
		Full Chamfer	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	3	
	450	Deburr	.00007	.00013	.00020	.00027	.00034	.00040	.00054	.00081	.00108	.00135	.00163	.00217	1	
		Edge Break	.00005	.00011	.00017	.00022	.00028	.00034	.00045	.00068	.00090	.00113	.00136	.00181	1	
		Full Chamfer	.00004	.00008	.00013	.00017	.00021	.00025	.00034	.00051	.00068	.00085	.00102	.00136	3	
	201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	200	Deburr	.00006	.00012	.00019	.00025	.00031	.00037	.00050	.00074	.00099	.00124	.00149	.00198	1
Edge Break			.00005	.00010	.00016	.00020	.00026	.00031	.00041	.00062	.00083	.00103	.00124	.00165	1	
Full Chamfer			.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	3	
150		Deburr	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	1	
		Edge Break	.00003	.00006	.00010	.00013	.00016	.00019	.00026	.00039	.00052	.00064	.00077	.00103	1	
		Full Chamfer	.00002	.00005	.00007	.00010	.00012	.00014	.00019	.00029	.00039	.00048	.00058	.00077	3	
TOOL STEELS	200	Deburr	.00006	.00012	.00019	.00025	.00031	.00037	.00050	.00074	.00099	.00124	.00149	.00198	1	
		Edge Break	.00005	.00010	.00016	.00020	.00026	.00031	.00041	.00062	.00083	.00103	.00124	.00165	1	
		Full Chamfer	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	3	
	150	Deburr	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	1	
		Edge Break	.00003	.00006	.00010	.00013	.00016	.00019	.00026	.00039	.00052	.00064	.00077	.00103	1	
		Full Chamfer	.00002	.00005	.00007	.00010	.00012	.00014	.00019	.00029	.00039	.00048	.00058	.00077	3	
	D, H, M, T, S series	150	Deburr	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	1
			Edge Break	.00003	.00006	.00010	.00013	.00016	.00019	.00026	.00039	.00052	.00064	.00077	.00103	1
			Full Chamfer	.00002	.00005	.00007	.00010	.00012	.00014	.00019	.00029	.00039	.00048	.00058	.00077	3
	TITANIUM ALLOYS	150	Deburr	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	1
Edge Break			.00003	.00006	.00010	.00013	.00016	.00019	.00026	.00039	.00052	.00064	.00077	.00103	1	
Full Chamfer			.00002	.00005	.00007	.00010	.00012	.00014	.00019	.00029	.00039	.00048	.00058	.00077	3	
HIGH TEMP ALLOYS	70	Deburr	.00004	.00008	.00012	.00015	.00019	.00023	.00031	.00046	.00062	.00077	.00093	.00124	1	
		Edge Break	.00003	.00006	.00010	.00013	.00016	.00019	.00026	.00039	.00052	.00064	.00077	.00103	1	
		Full Chamfer	.00002	.00005	.00007	.00010	.00012	.00014	.00019	.00029	.00039	.00048	.00058	.00077	3	
Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy																