

Speeds & Feeds

Product Table: End Mills for Steels & High Temp Alloys - Corner Radius - 2 & 3 Flute - Long Reach, Stub Flute Characteristics: 6x-6.9x Reach Multiple Series: MEF/MEFM

Material	Hardness (HBn)	SFM	Chip Load (IPT) By Cutter Diameter													Depth of Cut	
			0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	Radial	Axial	
Tool Steels: D, H, M, T, S series	350 - 400	100		.00010	.00015	.00019	.00024	.00029	.00058	.00078	.00312	.00123	.00164	.00327	1x Dia	.28x Dia	
	400 - 425	80	Slotting .00005														
Stainless Steels : 40x, 41x, 42x, 43x, 44x, 13-8, 15-5, 15-7, 17-4, 17-7	275 - 300	160															
	300 - 350	140		.00012	.00019	.00025	.00031	.00037	.00074	.00099	.00397	.00156	.00208	.00417	.28x Dia	.5x7x Dia	
Titanium: All alloys	275 - 300	200	Roughing .00006														
	300 - 350	125															
	350 - 400	75		.00016	.00024	.00032	.00041	.00048	.00097	.00130	.00520	.00205	.00273	.00546	.1x Dia	.5x - 1x Dia	
	400 - 425	75	Finishing .00008														
Nickel Alloys: Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	275 - 300	80															
	300 - 350	60		.00019	.00029	.00039	.00049	.00058	.00117	.00156	.00624	.00246	.00327	.00655	-	-	
	350 - 400	50	Max .00009														
	400 - 425	40															

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed. If you require additional information, Harvey Tool has a team of technical experts available to assist you through even themost challenging applications. Please contact us at **800-645-5609** or **Harveytech@harveyperformance.com**.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.