



Speeds & Feeds

Product Table: High Helix End Mills for Aluminum Alloys - 60° Helix - Square

Characteristics: 3x Length of Cut, 3 Flutes

Series: 7452xx, 7453xx, 7452xx-C8, 7453xx-C8

Cutter Series	MATERIAL	SFM	Chip Load Per Tooth (IPT) By Cutter Diameter									Depth of Cut		
			0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	Radial	Axial	
Uncoated	ALUMINUM ALLOYS													
	Casting (2xx, 5xx, 7xx, 8xx)	750	Slotting	.00012	.00026	.00039	.00051	.00065	.00077	.00104	.00155	.00208	1x Dia	.5x Dia
	Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000												
	MAGNESIUM ALLOYS	1500	Roughing	.00015	.00031	.00047	.00062	.00078	.00093	.00125	.00187	.00250	.5x Dia	.5x-1x Dia
	ZINC ALLOYS	800												
	COPPER ALLOYS													
	High Coppers - 90%+ (C1xxxx)	225												
	Brass (Copper Zinc alloys, C2xxxx, C3xxxx, C4xxxx, C66400-C69800)	500												
	Phosphor Bronzes (Copper Tin alloys, C5xxxx)	225												
	Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	500												
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500													
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxxx)	225													
Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95800, C97300-C97800, C99400-C99700)	550													
TiB2	ALUMINUM ALLOYS													
	Casting (2xx, 5xx, 7xx, 8xx)	1000	Slotting	.00016	.00033	.00051	.00067	.00084	.00100	.00135	.00202	.00270	1x Dia	.5x Dia
	Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1400												
	MAGNESIUM ALLOYS	2000	Roughing	.00020	.00040	.00061	.00081	.00101	.00121	.00163	.00243	.00325	.5x Dia	.5x-1x Dia
ZINC ALLOYS	1100													
			Finishing	.00011	.00022	.00033	.00043	.00055	.00065	.00088	.00131	.00175	.1x Dia	1x-3x Dia

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or harveytech@harveyperformance.com.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.