

Product Notes:
Due to a varying diameter, an Effective Cutter Diameter is needed for Chip Load selection and RPM calculation:
Effective Cutter Diameter = (Major Diameter + Minor Diameter)/2.
Or consider the actual diameter along the angle that is engaged with the workpiece.

Depth of Cut is shown as number of Passes with each pass resulting in a descending stepover

Chip Loads are given 3 ways:
Traditional Edge Break of .010"-.015"
Full Chamfer engagement for cutters with angles GREATER than 25° per side (50° included)
Full Chamfer engagement for cutters with angles LESS than 25° per side (50° included)

Chip Loads within table pertain to machining on one side of workpiece.
For machining on two sides, reduce Chip Loads to 60%-80% depending on contact length and finish
For vertical plunging, reduce Chip Loads to 40%-50% depending on finish

Material Guide		Hardness	SFM	Operation	Chip Load (IPT) By Effective Cutter Diameter												Depth of Cut	
					1/64	1/32	3/64	1/16	5/64	3/32	1/8	3/16	1/4	5/16	3/8	1/2	Passes	
Carbon Steel	10XX, 11XX, 12XX, 12LXX, ASTM A27, ASTM A36	29-37 Rc (279-344 HBn)	600	Edge Break	.00007	.00014	.00021	.00028	.00035	.00042	.00057	.00085	.00113	.00142	.00170	.00227	1	
				Full Chamfer (≥ 25°)	.00006	.00012	.00018	.00023	.00029	.00035	.00047	.00071	.00095	.00118	.00142	.00189	3	
				Full Chamfer (< 25°)	.00004	.00009	.00013	.00018	.00022	.00026	.00035	.00053	.00071	.00088	.00106	.00142	4	
Low Alloy Steel	13XX, 41XX, 43XX, 51XX, 86XX, 93XX	29-37 Rc (279-344 HBn)	200	Edge Break	.00006	.00013	.00019	.00026	.00032	.00039	.00052	.00078	.00104	.00129	.00156	.00207	1	
				Full Chamfer (≥ 25°)	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	3	
				Full Chamfer (< 25°)	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	4	
Tool Steel	A, L, O, P, W series	29-37 Rc (279-344 HBn)	200	Edge Break	.00006	.00013	.00019	.00026	.00032	.00039	.00052	.00078	.00104	.00129	.00156	.00207	1	
				Full Chamfer (≥ 25°)	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	3	
				Full Chamfer (< 25°)	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	4	
		38-45 Rc (353-421 HBn)	100	Edge Break	.00006	.00013	.00019	.00026	.00032	.00039	.00052	.00078	.00104	.00129	.00156	.00207	1	
				Full Chamfer (≥ 25°)	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	3	
				Full Chamfer (< 25°)	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	4	
	D, H, M, T, S series	29-37 Rc (279-344 HBn)	150	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	3	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	4	
		38-45 Rc (353-421 HBn)	75	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	4	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	5	
Austenitic Stainless Steel	Nitronic 50, Nitronic 60, 301, 303, 304, 304L, Incoloy 27-7MO, 316, 316L, 321, 347	29-37 Rc (279-344 HBn)	450	Edge Break	.00007	.00014	.00021	.00028	.00035	.00042	.00057	.00085	.00113	.00142	.00170	.00227	1	
				Full Chamfer (≥ 25°)	.00006	.00012	.00018	.00023	.00029	.00035	.00047	.00071	.00095	.00118	.00142	.00189	3	
				Full Chamfer (< 25°)	.00004	.00009	.00013	.00018	.00022	.00026	.00035	.00053	.00071	.00088	.00106	.00142	4	
Martensitic & Ferritic Stainless Steel	403, 410, 416, 420, 440, 430, 446	29-37 Rc (279-344 HBn)	200	Edge Break	.00006	.00013	.00019	.00026	.00032	.00039	.00052	.00078	.00104	.00129	.00156	.00207	1	
				Full Chamfer (≥ 25°)	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	3	
				Full Chamfer (< 25°)	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	4	
		38-45 Rc (353-421 HBn)	100	Edge Break	.00006	.00013	.00019	.00026	.00032	.00039	.00052	.00078	.00104	.00129	.00156	.00207	1	
				Full Chamfer (≥ 25°)	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	4	
				Full Chamfer (< 25°)	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	5	
PH Stainless Steel	15-5, 17-4, Carpenter 450, Carpenter 465	29-37 Rc (279-344 HBn)	150	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	3	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	4	
		38-45 Rc (353-421 HBn)	90	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	4	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	5	
Nickel Alloy	Hastelloy C-22, Inconel 625, Waspaloy, René 41, Inconel 718, Incoloy 20	29-37 Rc (279-344 HBn)	70	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	3	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	4	
		38-45 Rc (353-421 HBn)	50	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	4	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	5	
Titanium Alloy	Ti 3Al-2.5V, Ti 6Al-4V, Ti 10V-2Fe-3Al	29-37 Rc (279-344 HBn)	150	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	3	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	4	
		38-45 Rc (353-421 HBn)	75	Edge Break	.00004	.00008	.00012	.00016	.00020	.00024	.00032	.00048	.00065	.00081	.00097	.00130	1	
				Full Chamfer (≥ 25°)	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	4	
				Full Chamfer (< 25°)	.00002	.00005	.00008	.00010	.00013	.00015	.00020	.00030	.00041	.00051	.00061	.00081	5	
Wrought Aluminum Alloy	2014, 5062, 6061, 7050, 7075, 7475	≤ 28 Rc (≤ 271 HBn)	1000	Edge Break	.00018	.00037	.00056	.00074	.00094	.00112	.00150	.00224	.00300	.00374	.00450	.00600	1	
				Full Chamfer (≥ 25°)	.00015	.00031	.00047	.00062	.00078	.00093	.00125	.00187	.00250	.00312	.00375	.00500	2	
				Full Chamfer (< 25°)	.00011	.00023	.00035	.00047	.00059	.00070	.00094	.00140	.00188	.00234	.00281	.00375	3	
	5% - 8% Si (400XX)		1000	Edge Break	.00016	.00033	.00051	.00067	.00084	.00100	.00135	.00202	.00270	.00337	.00405	.00540	1	
				Full Chamfer (≥ 25°)	.00014	.00028	.00042	.00056	.00070	.00084	.00113	.00168	.00225	.00281	.00338	.00450	2	
				Full Chamfer (< 25°)	.00010	.00021	.00032	.00042	.00053	.00063	.00084	.00126	.00169	.00211	.00253	.00338	3	
Cast Aluminum Alloy	319.0, 328.0, 355.0, 360.0, 380.0, 383.0, 390.0, 520.0, 535.0		750	Edge Break	.00018	.00037	.00056	.00074	.00094	.00112	.00150	.00224	.00300	.00374	.00450	.00600	1	
				Full Chamfer (≥ 25°)	.00015	.00031	.00047	.00062	.00078	.00093	.00125	.00187	.00250	.00312	.00375	.00500	2	
				Full Chamfer (< 25°)	.00011	.00023	.00035	.00047	.00059	.00070	.00094	.00140	.00188	.00234	.00281	.00375	3	
	3% - 5% Si (30X, A30X, C30X, 40X, A40X, B40X)	≤ 28 Rc (≤ 271 HBn)	750	Edge Break	.00016	.00033	.00051	.00067	.00084	.00100	.00135	.00202	.00270	.00337	.00405	.00540	1	
				Full Chamfer (≥ 25°)	.00014	.00028	.00042	.00056	.00070	.00084	.00113	.00168	.00225	.00281	.00338	.00450	2	
				Full Chamfer (< 25°)	.00010	.00021	.00032	.00042	.00053	.00063	.00084	.00126	.00169	.00211	.00253	.00338	3	
	5% - 8% Si (30X, A30X, C30X, 40X, A40X, B40X)		700	Edge Break	.00018	.00037	.00056	.00074	.00094	.00112	.00150	.00224	.00300	.00374	.00450	.00600	1	
				Full Chamfer (≥ 25°)	.00014	.00028	.00042	.00056	.00070	.00084	.00113	.00168	.00225	.00281	.00338	.00450	2	
8% - 12% Si (30X, A30X, C30X, 40X, A40X, B40X)		650	Full Chamfer (≥ 25°)	.00014	.00028	.00042	.00056	.00070	.00084	.00113	.00168	.00225	.00281	.00338	.00450	2		
			475	Full Chamfer (< 25°)	.00010	.00021	.00032	.00042	.00053	.00063	.00084	.00126	.00169	.00211	.00253	.00338	3	
Copper Alloy	Cu-ETP, CuBe2, CuZn30, CuZn36Pb3, CuZn10, CuSn5	≤ 28 Rc (≤ 271 HBn)		225-500	Edge Break	.00014	.00030	.00045	.00060	.00075	.00089	.00120	.00180	.00240	.00300	.00360	.00480	1
			Full Chamfer (≥ 25°)		.00012	.00025	.00038	.00050	.00062	.00074	.00100	.00150	.00200	.00250	.00300	.00400	2	
			Full Chamfer (< 25°)		.00009	.00019	.00028	.00037	.00047	.00056	.00075	.00112	.00150	.00187	.00225	.00300	3	
Magnesium Alloys		≤ 28 Rc (≤ 271 HBn)	1500	Edge Break	.00018	.00037	.00056	.00074	.00094	.00112	.00150	.00224	.00300	.00374	.00450	.00600	1	
Zinc Alloys	800		Full Chamfer (≥ 25°)	.00015	.00031	.00047	.00062	.00078	.00093	.00125	.00187	.00250	.00312	.00375	.00500	2		
		Full Chamfer (< 25°)	.00011	.00023	.00035	.00047	.00059	.00070	.00094	.00140	.00188	.00234	.00281	.00375	3			