Speeds & Feeds

Product Table: Miniature End Mills - Tapered - Square
Characteristics: 5°-6° Angle per Side, 8x Length of Cut
Series: 7608xx

Product Notes:
Use the end diameter of the tool to select the correct Chip Load (IPT)

General Notes:
All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 10%-20% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 10%-20%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or **Harveytech@harveyperformance.com**

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and

Hardness: ≤ 28 Rc (≤ 271 HBn)

MATERIAL	SFM	Chip Load (IPT) By Cutter Dia				Depth of Cut		Chip Load (IPT) By Cutter Dia						Depth of Cut	
		.015	.031	.047		Radial	Axial	.062	.078	.093	.125	.187	.250	Radial	Axial
ALUMINUM ALLOYS															
Casting (2xx, 5xx, 7xx, 8xx)	750	Finishing	.00030	.00062	.00094	.05 x Dia	8 x Dia	.00108	.00136	.00162	.00217	.00325	.00435	.10 x Dia	8 x Dia
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000														
Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	750	Finishing	.00027	.00056	.00085	.05 x Dia	8 x Dia	.00097	.00122	.00145	.00196	.00293	.00391	.10 x Dia	8 x Dia
Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	700														
Casting - 8%-12% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	650														
Casting - 12%-16% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	475														
Wrought - 5%-8% Si (4xxx)	1000														
Wrought - 8%-12% Si (4xxx)	800														
MAGNESIUM ALLOYS	1500	Finishing	.00030	.00062	.00094	.05 x Dia	8 x Dia	.00108	.00136	.00162	.00217	.00325	.00435	.10 x Dia	8 x Dia
ZINC ALLOYS	800														
COPPER ALLOYS															
High Coppers - 90%+ (C1xxxx)	225	Finishing	.00024	.00050	.00075	.05 x Dia	8 x Dia	.00086	.00108	.00129	.00174	.00260	.00348	.10 x Dia	8 x Dia
Brass (Copper Zinc alloys, C2xxxx, C3xxxx, C4xxxx, C66400-C69800)	500														
Phosphor Bronzes (Copper Tin alloys, C5xxxx)	225														
Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	500														
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500														
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxxx)	225														
Cast Copper Alloys (C83300-C86200, C86400-C87900, C92200-C95800, C97300-C97800, C99400-C99700)	550														

Hardness: 29-37 Rc (279-344 HBn)

MATERIAL	SFM	Chip Load (IPT) By Cutter Dia				Depth of Cut		Chip Load (IPT) By Cutter Dia						Depth of Cut	
		.015	.031	.047		Radial	Axial	.062	.078	.093	.125	.187	.250	Radial	Axial
CARBON STEELS															
Free-Machining/Low Carbon steels, 10xx - 1029 & all 10Lxx, 11xx - 1139 & all 11Lxx, 12xx - 1215 & all 12Lxx	600	Finishing	.00009	.00019	.00029	.05 x Dia	8 x Dia	.00034	.00042	.00051	.00068	.00102	.00136	.10 x Dia	8 x Dia
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xxx, 3xxx, 4xxx & 4xLxx, 5xxx & 5xLxx, 50xxx & 50Lxxx, 51xxx & 51Lxxx, 52xxx & 52Lxxx, 6xxx, 8xxx, 9xxx	200	Finishing	.00009	.00018	.00027	.05 x Dia	8 x Dia	.00031	.00039	.00046	.00062	.00093	.00124	.10 x Dia	8 x Dia
STAINLESS STEELS															
203 EZ, 303 (all types), 416, 416Se, 416 Plus X, 420F, 420FSe, 430F, 430FSe, 440F, 440FSe	450	Finishing	.00009	.00019	.00029	.05 x Dia	8 x Dia	.00034	.00042	.00051	.00068	.00102	.00136	.10 x Dia	8 x Dia
201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	200	Finishing	.00009	.00018	.00027	.05 x Dia	8 x Dia	.00031	.00039	.00046	.00062	.00093	.00124	.10 x Dia	8 x Dia
414, 431, 440A, 440B, 440C, 13-8, 15-5, 15-7, 17-4, 17-7	150	Finishing	.00005	.00011	.00017	.05 x Dia	8 x Dia	.00019	.00024	.00029	.00039	.00058	.00078	.10 x Dia	8 x Dia
TOOL STEELS															
A, L, O, P, W series	200	Finishing	.00009	.00018	.00027	.05 x Dia	8 x Dia	.00031	.00039	.00046	.00062	.00093	.00124	.10 x Dia	8 x Dia
D, H, M, T, S series	150	Finishing	.00005	.00011	.00017	.05 x Dia	8 x Dia	.00019	.00024	.00029	.00039	.00058	.00078	.10 x Dia	8 x Dia
TITANIUM ALLOYS	150	Finishing	.00005	.00011	.00017	.05 x Dia	8 x Dia	.00019	.00024	.00029	.00039	.00058	.00078	.10 x Dia	8 x Dia
HIGH TEMP ALLOYS															
Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	70	Finishing	.00005	.00011	.00017	.05 x Dia	8 x Dia	.00019	.00024	.00029	.00039	.00058	.00078	.10 x Dia	8 x Dia

Hardness: 38-45 Rc (353-421 HBn)

SFM	Chip Load (IPT) By Cutter Dia				Depth of Cut		Chip Load (IPT) By Cutter Dia						Depth of Cut	
		.015	.031	.047	Radial	Axial	.062	.078	.093	.125	.187	.250	Radial	Axial
-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
100	Finishing	.00004	.00009	.00014	.05 x Dia	8 x Dia	.00016	.00020	.00023	.00031	.00047	.00063	.10 x Dia	8 x Dia
90	Finishing	.00003	.00006	.00008	.05 x Dia	8 x Dia	.00010	.00012	.00015	.00020	.00029	.00039	.10 x Dia	8 x Dia
100	Finishing	.00004	.00009	.00014	.05 x Dia	8 x Dia	.00016	.00020	.00023	.00031	.00047	.00063	.10 x Dia	8 x Dia
90	Finishing	.00003	.00006	.00008	.05 x Dia	8 x Dia	.00010	.00012	.00015	.00020	.00029	.00039	.10 x Dia	8 x Dia
75	Finishing	.00003	.00006	.00008	.05 x Dia	8 x Dia	.00010	.00012	.00015	.00020	.00029	.00039	.10 x Dia	8 x Dia
50	Finishing	.00003	.00006	.00008	.05 x Dia	8 x Dia	.00010	.00012	.00015	.00020	.00029	.00039	.10 x Dia	8 x Dia