

SPEEDS & FEEDS

HEVF-C-5

Combination Feed & HEM- 5 Flute

HEVF-C-5																	
Material Guide		Hardness	SFM	Inches Per Tooth (IPT)													
				1/8		3/16		1/4		3/8		1/2		3/4		1	
				Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh	Slot	Rgh
CARBON STEEL	10XX, 11XX, 12XX, 12LXX, ASTM A27, ASTM A36	< 75 HRB	455	.0027	.0015	.0040	.0021	.0053	.0029	.0080	.0043	.0107	.0056	.0160	.0080	.0214	.0102
		75 - 98 HRB	445	.0020	.0011	.0030	.0015	.0040	.0021	.0060	.0031	.0080	.0041	.0120	.0059	.0160	.0075
		21 - 36 HRC	400	.0013	.0007	.0020	.0010	.0027	.0014	.0040	.0020	.0053	.0026	.0080	.0038	.0106	.0048
LOW ALLOY STEEL	13XX, 41XX, 43XX, 51XX, 86XX, 93XX	75 - 98 HRB	390	.0027	.0009	.0040	.0013	.0053	.0018	.0080	.0027	.0107	.0035	.0160	.0051	.0214	.0065
		21 - 36 HRC	340	.0027	.0007	.0040	.0010	.0053	.0013	.0080	.0020	.0107	.0026	.0160	.0038	.0214	.0048
		36 - 50 HRC	260	.0020	.0006	.0030	.0009	.0040	.0012	.0060	.0017	.0080	.0023	.0120	.0033	.0160	.0042
		> 50 HRC	155	.0013	.0005	.0020	.0007	.0027	.0009	.0040	.0014	.0053	.0018	.0080	.0026	.0106	.0033
TOOL STEEL	A2, H13, L6, P20, S7	75 - 98 HRB	340	.0027	.0009	.0040	.0013	.0053	.0018	.0080	.0027	.0107	.0035	.0160	.0051	.0214	.0065
		21 - 36 HRC	250	.0027	.0007	.0040	.0011	.0053	.0015	.0080	.0022	.0107	.0028	.0160	.0040	.0214	.0051
		36 - 50 HRC	145	.0020	.0006	.0030	.0008	.0040	.0011	.0060	.0017	.0080	.0022	.0120	.0031	.0160	.0040
		> 50 HRC	85	.0013	.0005	.0020	.0007	.0027	.0009	.0040	.0014	.0053	.0018	.0080	.0026	.0106	.0033
SPECIALTY STEEL	300M, Invar 36, Kovar, Maraging 200, Maraging 250, Maraging 300, Maraging 350	< 75 HRB	290	.0027	.0012	.0040	.0018	.0053	.0024	.0080	.0035	.0107	.0046	.0160	.0066	.0214	.0085
		75 - 98 HRB	255	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0024	.0107	.0032	.0160	.0045	.0214	.0058
		21 - 36 HRC	175	.0027	.0008	.0040	.0011	.0053	.0015	.0080	.0022	.0107	.0029	.0160	.0041	.0214	.0052
		36 - 50 HRC	150	.0020	.0007	.0030	.0010	.0040	.0013	.0060	.0019	.0080	.0026	.0120	.0037	.0160	.0046
		> 50 HRC	55	.0013	.0004	.0020	.0006	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0022	.0106	.0029
AUSTENITIC STAINLESS STEEL	Nitronic 50, Nitronic 60, 301, 303, 304, 304L, Incoloy 27-7MO, 316, 316L, 321, 347	75 - 98 HRB	265	.0027	.0009	.0040	.0013	.0053	.0018	.0080	.0026	.0107	.0034	.0160	.0049	.0214	.0063
		21 - 36 HRC	225	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0024	.0107	.0031	.0160	.0044	.0214	.0057
		36 - 50 HRC	180	.0022	.0007	.0033	.0009	.0043	.0013	.0065	.0019	.0087	.0025	.0130	.0036	.0174	.0045
MARTENSITIC & FERRITIC STAINLESS STEEL	403, 410, 416, 420, 440, 430, 446	75 - 98 HRB	300	.0025	.0009	.0038	.0013	.0050	.0018	.0075	.0027	.0100	.0035	.0150	.0051	.0200	.0065
		21 - 36 HRC	280	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0024	.0107	.0031	.0160	.0044	.0214	.0056
PH STAINLESS STEEL	15-5, 17-4, Carpenter 450, Carpenter 465	21 - 36 HRC	200	.0025	.0007	.0038	.0010	.0050	.0013	.0075	.0020	.0100	.0026	.0150	.0037	.0200	.0048
		36 - 50 HRC	145	.0020	.0006	.0030	.0009	.0040	.0012	.0060	.0017	.0080	.0023	.0120	.0032	.0160	.0041
GRAY CAST IRON	SAE J431, ASTM A48	75 - 98 HRB	410	.0027	.0015	.0040	.0022	.0053	.0029	.0080	.0044	.0107	.0057	.0160	.0082	.0214	.0104
		21 - 36 HRC	370	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0024	.0107	.0031	.0160	.0045	.0214	.0057
MALLEABLE CAST IRON	ASTM A47, ASTM A220, ASTM A602	75 - 98 HRB	345	.0027	.0010	.0040	.0014	.0053	.0019	.0080	.0028	.0107	.0036	.0160	.0052	.0214	.0066
		21 - 36 HRC	335	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0024	.0107	.0031	.0160	.0045	.0214	.0057
NODULAR (DUCTILE) CAST IRON	ASTM A536, ASTM 897	75 - 98 HRB	310	.0027	.0010	.0040	.0014	.0053	.0020	.0080	.0029	.0107	.0038	.0160	.0054	.0214	.0069
		21 - 36 HRC	260	.0027	.0007	.0040	.0010	.0053	.0013	.0080	.0019	.0107	.0025	.0160	.0036	.0214	.0046
		36 - 50 HRC	135	.0013	.0004	.0020	.0006	.0027	.0008	.0040	.0012	.0053	.0016	.0080	.0023	.0106	.0029
PURE NICKEL	Nickel 200, Nickel 201	< 75 HRB	285	.0027	.0013	.0040	.0018	.0053	.0025	.0080	.0037	.0107	.0049	.0160	.0070	.0214	.0089
		75 - 98 HRB	250	.0027	.0011	.0040	.0015	.0053	.0021	.0080	.0031	.0107	.0041	.0160	.0058	.0214	.0074
NICKEL ALLOY	Hastelloy C-22, Inconel 625, Waspaloy, René 41, Inconel 718, Incoloy 20	75 - 98 HRB	80	.0027	.0006	.0040	.0009	.0053	.0013	.0080	.0019	.0107	.0025	.0160	.0035	.0214	.0045
		21 - 36 HRC	75	.0027	.0006	.0040	.0009	.0053	.0012	.0080	.0018	.0107	.0024	.0160	.0034	.0214	.0043
		36 - 50 HRC	70	.0022	.0005	.0033	.0008	.0043	.0010	.0065	.0015	.0087	.0020	.0130	.0029	.0174	.0037
PURE TITANIUM	Ti Grade 1, Ti Grade 2, Ti Grade 3, Ti Grade 4, Ti Grade 7, Ti Grade 12	< 75 HRB	300	.0027	.0017	.0040	.0025	.0053	.0035	.0080	.0051	.0107	.0067	.0160	.0096	.0214	.0122
		75 - 98 HRB	275	.0027	.0015	.0040	.0021	.0053	.0029	.0080	.0043	.0107	.0056	.0160	.0081	.0214	.0103
		21 - 36 HRC	250	.0027	.0011	.0040	.0016	.0053	.0022	.0080	.0032	.0107	.0042	.0160	.0060	.0214	.0077
TITANIUM ALLOY	Ti 3Al-2.5V, Ti 6Al-4V, Ti 10V-2Fe-3Al	21 - 36 HRC	180	.0027	.0009	.0040	.0013	.0053	.0017	.0080	.0025	.0107	.0033	.0160	.0048	.0214	.0061
		36 - 50 HRC	160	.0025	.0008	.0038	.0012	.0050	.0016	.0075	.0023	.0100	.0030	.0150	.0043	.0200	.0055
COBALT ALLOY	ASTM F562, ASTM F90, ASTM F75, ASTM F799	75 - 98 HRB	210	.0020	.0007	.0030	.0011	.0040	.0015	.0060	.0021	.0080	.0028	.0120	.0040	.0160	.0051
		21 - 36 HRC	170	.0027	.0007	.0040	.0010	.0053	.0014	.0080	.0021	.0107	.0027	.0160	.0039	.0214	.0050
		36 - 50 HRC	65	.0020	.0005	.0030	.0007	.0040	.0010	.0060	.0014	.0080	.0018	.0120	.0026	.0160	.0034

Milling Process	Hardness	ADOC	RDOC
Slot (Full Slotting)	< 35 HRC	3.00%-5.00% Diameter	100% Diameter
	≥ 35 HRC	2.50%-4.00% Diameter	100% Diameter
Rgh (Traditional Roughing)	< 35 HRC	Up to Max LOC	15%-30% Diameter
	≥ 35 HRC	Up to Max LOC	10%-20% Diameter

Note: IPT values shown are for 2.5xD length of cut tools, and should be adjusted for longer or shorter lengths of cut. For more accurate running parameters, please refer to Machining Advisor Pro.