

Speeds & Feeds

Product Table: End Mills for Hardened Steels - Finisher - Ball **Characteristics:** 5x Reach Multiple, 3 Flutes **Series:** 8129xx-C6, 8130xx-C6

| Material | Hardness | SFM | Chip Load (IPT) By Cutter Diameter | | | | | | | | | | | | | Depth of Cut | |
|-----------------|----------|-----|------------------------------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------------|-----------|
| | | | | .015 | .031 | .047 | .062 | .078 | .093 | .125 | .187 | .250 | .312 | .375 | .500 | Radial | Axial |
| Hardened Steels | 45-55 Rc | 700 | Finishing | .00021 | .00044 | .00066 | .00087 | .00110 | .00131 | .00176 | .00263 | .00351 | .00438 | .00527 | .00702 | .10 x Dia | .04 x Dia |
| | 56-68 Rc | 600 | Finishing | .00017 | .00035 | .00053 | .00070 | .00088 | .00104 | .00140 | .00210 | .00281 | .00350 | .00421 | .00562 | .07 x Dia | .04 x Dia |

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or **Harveytech@harveyperformance.com**.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.